



SCREEN PRINTING

UV INK

UViprim GL-BC

The two components UViprim GL-BC ink is the best choice for high speed screen printing on glass, with or without coating, for indoor use. The main assets of UViprim GL-BC inks are their gloss, very high reactivity, chemical and dishwasher resistance. There is no need of thermic treatment.

Use

Preparation of ink:

UViprim GL-BC is a two components UV screen printing, so add 4% of catalyst (**ref. 3460565**) to the ink, stir homogeneously and wait 30 min before printing.

The mixture has a pot life of 8 hours at room temperature (20-25°C). Higher temperature reduce the pot life.

Choice of the screens:

Directly function of the printing speed and the desired opacity.

Generally, one will use a 165 to 120 mesh (420-305 threads/inch) fabric tended to 16N. The diameter of the wire will be selected to obtain the best compromise between the deposit, the solidity and the definition.

Characteristics

- Glossy
- Resists on dish washing
- Heavy metal free
- Basic shades are intermixable and allow the matching of color reference systems like Pantone®
- High reactivity
- Resistance to alcohol , G1 test blend and alkali
- Do not require thermal post treatment

Supports and pretreatments

The quality of glass and its chemical structure are related to its manufacturing method. Its surface quality will have to be perfect i.e. free from release agent or any other residue (finger marks, dust, grease, silicone etc).

Untreated glass:

A flame treatment (surface tension > 44 mN/m) according to the UVitro® process (trade mark of ISIMAT GmbH) is necessary to obtain maximum performances.

Coated glass:

Many glass containers are covered with a water or solvent-based coating to modify the surface aspect (colour, opalescent, scratch resistance...): a flame treatment, right before printing, is then essential to obtain a sufficient surface tension and thus a good adherence.

Curing conditions

All the colours can be cured under a medium pressure mercury lamp of 180-200W/cm. Optimal adhesion is achieved after 24-48H at room temperature.

The performances of the system are function of the material and the products used. Its industrial validation is imperative before final production run.

The type of reflector, UV lamps, the colours of glass, the thickness of printed ink influence the polymerization process and the adhesion of the ink.

Before printing, a pre-treatment of the glass (flame or UVitro® or PYROSIL®) improve the adherence of the ink.

Specifications

- | | |
|---|--|
| <ul style="list-style-type: none"> ➤ Appearance: glossy ➤ Average density: 1,2 ➤ Viscosity: 5 ± 1 Pa.s ➤ Opacifying power: <ul style="list-style-type: none"> • Coloriflex system: low • Opaque inks: excellent • White, black: excellent | <ul style="list-style-type: none"> ➤ Thinner: 31970NG*, 5 % maxi ➤ Cleaning solvent: 2891, 2899, NS-91 and NS-99 ➤ Expiry: refer to the label |
|---|--|

*diluent 31970NG : Skin irritation, Category 2 ; Eye irritation, Category 2, Skin sensitisation, Category 1

Toxicology

The **UViprim GL-BC** inks comply with EN 71-3 standard.

STANDARD COLOURS		Ref. 1 kg
COLORIFLEX SYSTEM		
	Lemon*	3462002
	Gold yellow*	3462004
	Orange*	3462006
	Scarlet*	3462007
	Red*	3462008
	Cyclamen*	3462014
	Purple / Violet*	3462016
	Blue*	3462020
	Royal blue*	3462028
	Green*	3462032

EXTRA OPAQUE		Ref. 1 kg
	Opaque white*	3462080
	Opaque lemon	3462082
	Opaque orange	3462083
	Opaque red	3462084
	Opaque green	3462085
	Opaque black*	3462081

Non contractual colours and pictures
On simple request, we can propose you a color panel card displaying accurate shades.

[Pantone® colour matching](#)

All the marked inks with an asterisk *, can be colour matched according to the Pantone® colour guide through the online Colour Matching System developed by Tiflex.

Additives

OPALESCENT BASE: its use in inks lightens the colour while increasing the reactivity and opalescence by transmission with a loss of brilliance.

METALLIC INKS: to use the diluting base with our metallic pastes in a 85/15 or 80/20 proportion. The shelf-life of the blend is of 4 hours.

- | | |
|-------------------|------|
| Photoinitiator: | 1-3% |
| Gelling agent: | 0-1% |
| Thickener powder: | 0-1% |

STANDARD COLOURS		Ref. 1 kg
4-COLOURS PROCESS		
4-colours yellow		3462050
4-colours magenta		3462052
4-colours cyan		3462054
4-colours black		3462056
TINTING		
Tinting white		3462042
Tinting black		3462044

BASE		Ref. 1 kg
Thinner base*		3462066
ADDITIVES		
Catalyst, 100 gr		3460564
Catalyst, per kg		3462064
New generation catalyst, 100 gr		3460565
Opalescent varnish		3462068
Etching varnish		3462069
Window varnish		3462067
Photoinitiator, per 100 g		38C0595
Gelling agent		3952061
Thickener powder		3761295

Also available in metallic, pearlescent, fluorescent, iridescent, two-tones, etc ... shades. Please, contact us for details.



IMP. TIFLEX. 05.02.2018 - Non contractual colours and pictures - Only our Web-site is authorised to give real-time information about our inks. Paper notices are considered unwritten and no longer engage our company's responsibility once they are updated on our Web-site. Our responsibility can be engaged only if the customer has based his position on the information published on our Web-site. In all cases, the user should carry out validation tests under his own conditions before using our inks for his production. The safety data sheets are available free of charge at: www.tiflex.com/fds

