



Reusche Colors

Blendable Bending Colors

Profile:

High gloss, opaque, vibrant color

Firing Temperature:

1200-1300°F (649-704C) Firing cycles may vary based on kiln size, load size, substrate, etc.

Mixibility:

All colors within the range are fully intermixable,
Testing recommended.

Application:

Supplied as powder or pastes for screen printing, either hot or cold,
and for hand painting.

Health & Safety:

For detailed Health and Safety requirements consult the appropriate
Material Safety Data Sheets.



These colors contain lead and/or cadmium. Do not use on food bearing surfaces, toys or children's items.

Reusche Colors

Blendable Bending Colors





Recommended Firing Temperature 1200-1300F

Product Number	Description	Color Swatch
D201581	White	N/A
D211824	Yellow Red	
D211827	Blue Red	
D211831	Maroon	
D281097	Orange	
D232782	Green Yellow	
D232792	Gold Yellow	
D232786	Orange Yellow	
D252174	Green	
D261935	Chrome Green	
D261939	Blue Green	
D273889	Green Blue	
D273893	Red Blue	
D273908	Dark Blue	
D293363	Buff	
D293360	Brown	

Reusche Colors

Blendable Bending Colors

Recommended Firing Temperature 1200-1300F

Product Number	Description	Color Swatch
D293355	Red Brown	
D293376	Dark Brown	
D293371	Dark Brown	
D242013	Black	

The quoted Pantone® reference is provided as a guide to the potential color. Pantone® is a registered trademark of Pantone Inc. Actual color may vary depending on individual monitor settings and cannot be guaranteed.