



Reusche Colors

High Gloss Overglaze - Unleaded

Profile:

Full gloss, opaque.

Firing Temperature:

1250-1450°F (676-788C) Firing cycles are dependent on the type and thickness of the glass in addition to kiln size and load.

Mixibility:

All colors within the range are fully intermixable,
Testing recommended.

Application:

Supplied as powder or pastes for screen printing, either hot or cold, and for hand painting.

Health & Safety:

For detailed Health and Safety requirements consult the appropriate Material Safety Data Sheets.



Formulated without lead or cadmium (unless otherwise stated). Lead not added intentionally.

Reusche Colors

High Gloss Overglaze - Unleaded

Recommended Firing Temperature 1250-1450F

Product Number	Description	Color Swatch
HGU5015	Green	
HGU5018	Tropical Green	
HGU5017	Deep Ocean	
HGU5014	Flag Blue	
HGU5016	Ginger Bread	
HGU5012	Rustic Brown	
HGU5013	Dark Earth	
HGU5011	Raven Black	
HGU5005	White	
HGU5001	Flux	