



Reusche Colors

Preferred Leaded Colors

Profile:

Glass enamels, exhibiting high gloss.

Firing Temperature:

1120-1160°F (600-630C) Firing cycles are dependent on the type of thickness of the glass, size and type of kiln, kiln load, Lehr and belt speed.

Mixibility:



All colors within the range are fully intermixable. However, we recommend running pre-production tests to verify color stability.

Application:

Supplied as powder or pastes for screen printing, either hot or cold, and spraying.

Health & Safety:











For detailed Health and Safety requirements consult the appropriate Material Safety Data Sheets.

	These colors contain lead and/or cadmium. Do not use on food bearing surfaces, toys or children's items.
	Dishwasher durability is high.

Reusche Colors

Preferred Leaded Colors




Recommended Firing Temperature 1120-1160F

Product Number	Description	Color Swatch
61R022	Flux	N/A
61R010	Etch	N/A
61R012	White	N/A
61R013	Vivid White	N/A
65R043	Pagoda Red	
65R050	Torch Red	
65R510	Ruby Red	
62R521	Orange	
62R522	Dutch Orange	
62R028	Yellow	
62R029	Yellow	
62R023	Sunlight	
63R071	Green	
63R511	Chrome Green	

Reusche Colors

Preferred Leaded Colors

Recommended Firing Temperature 1120-1160F

Product Number	Description	Color Swatch
63R072	Green	
64R062	Turquoise	
64R058	Blue	
64R056	Blue	
66R047	Autumn Brown	
66R045	Chocolate Brown	
67R010	Black	
67R020	Dense Black	